

# TARMAC

## COLOURED PRESSURE POINTING MORTARS

### DESCRIPTION

**Tarmac Coloured Pressure Pointing Mortar** is a Portland cement based mortar designed to provide a gun injected mortar that is water resistant and suitable for most masonry applications.

**Tarmac Coloured Pressure Pointing Mortar** is available in eleven standard colours- each one carefully chosen to complement the natural stone and brick tones predominating throughout the United Kingdom.

### USES

**Tarmac Coloured Pressure Pointing Mortar** is specifically designed for use in paving, brickwork, blockwork and landscaping applications. It produces a high quality, durable finish with a high level of resistance to a variety of climatic conditions.

### SPECIAL PROPERTIES

#### **Tarmac Coloured Pressure Pointing Mortar**

- Low Water Absorption.
- Non-Shrink.
- High Quality Finish.

### TYPICAL PERFORMANCE

Compressive Strength N/mm<sup>2</sup> (at 20 deg C)

	1 day	3 days	7 days	28 days
	18	30	40	45

Dark Grey 30n

	10	16	22	30
--	----	----	----	----

### STANDARD COLOUR RANGE

**Tarmac Coloured Pressure Pointing Mortar** is available in the following colours:

1. Standard
2. Black
3. Brick Red
4. Dark Brown
5. Buff
6. White
7. Yorkstone
8. Sandstone
9. Dark Grey (45n & 30n)
10. Light Brown
11. Light Grey

Water Solids Ratio:

Standard, Black, Buff, White, Light Brown, Light Grey

0.16 = 4 litres/25kg bag of powder

Brick Red, Dark Brown, Yorkstone, Sandstone, Dark Grey

0.17 = 4.25 litres/25kg bag of powder

Usable Life: 60 minutes from adding water

Initial Set: 45n            3 hrs  
Initial Set: 30n            4 hrs 30 mins

Yield: At 0.16 approx 13.75L/25kg powder  
At 0.17 approx 14.00L/25kg powder

### **MIXING INSTRUCTIONS**

**Tarmac Coloured Pressure Pointing Mortar** should be mixed using water, which complies with BS EN 1008 (as for concrete).

**Tarmac Coloured Pressure Pointing Mortar** should be efficiently mixed in a suitable container using either an electric (1Kw) or pneumatic power tool, but can be mixed by hand if necessary.

A 25kg bag of **Tarmac Coloured Pressure Pointing Mortar** should be carefully poured and mixed into the water.

Leave the mortar to stand for 20 minutes and then remix and add further water to achieve the correct consistency. Up to 0.5 litres of water may be added to achieve the correct consistency.

### **PLACING**

**Tarmac Coloured Pressure Pointing Mortar** may be placed by a hand gun injection, trowel or other mechanical pointing equipment.

### **PACKAGING & STORAGE**

**Tarmac Coloured Pressure Pointing Mortar** is available in nominal 25kg sacks palletised and shrinkwrapped. Alternative packing may be available upon request.

**Tarmac Coloured Pressure Pointing Mortar** should be stored in cool dry areas clear of the ground sheeted, or under cover and stacked not more than 2 pallets high.

The product should be used on a first in – first out basis.

Shelf life is minimum 3 months when properly stored but could be in excess of 6 months subject to temperature and humidity.

### **HEALTH & SAFETY**

See separate data sheet reference 28/A.

### **QUALITY CONTROL**

Factory blended, tested and packaged in the UK for Adomast Ltd to quality control procedure in accordance with BS EN ISO 9001 Series.