

# ADOCURE SEALER PF

## Concrete Curing & Sealing Compound for Power Floated Floors

### Description

A clear acrylic polymer resin solution for application to surfaces of freshly laid concrete floors that have been finished by power floating. It has a double function, firstly to form a highly effective curing membrane that conforms to ASTM. C309 and secondly to act as an in-depth sealer for the hardened concrete. It gives a surface that is dustproof and extremely hard wearing.

### Benefits

- Cures and seals in one operation saving time and labour.
- Ideal for use in fast-track construction
- Curing efficiency 75% in accordance with ASTM. C309
- Provides abrasion resistant hard wearing easy-clean surface
- Effective anti-carbonation coating
- Permits bond of most subsequent coatings intended for concrete

### Instructions for use

Apply by fan-jet sprayer to achieve a typical coverage of 12m<sup>2</sup> per litre immediately after final finishing and when surface water is no longer evident.

Avoid over application, **ADOCURE SEALER PF** should not be allowed to form 'puddles' but to just leave a wet gloss appearance.

### Sprayer cleaning

Immediately after spraying, clean line and nozzle thoroughly with white spirit. If not possible to carry out immediately, or if sprayer has been standing, clean with **RESOKLENS**.

### Overcoating

In general most paints and cement grouts will adhere well to concrete treated with **ADOCURE SEALER PF**, but to ensure compatibility it is advisable to first apply a test patch.

### Typical data

Touch Dry Time:	2 to 4 hours dependent upon temperature and wind
Hard Dry Time:	18 to 24 hours dependent upon temperature and wind
Curing Efficiency:	75% @ 12m <sup>2</sup> per litre
Flash Point:	40°C

### Packaging

210 and 25 litre containers

### Storage

Keep containers sealed. Store in dry conditions at room temperature and away from direct heat. All applicable storage requirements for flammable materials should be observed. When stored correctly in unopened container storage stability is 1 year

## Concrete Surface Treatments

### Health and Safety

Material is flammable. Avoid physical contact with material and inhalation. If contact with skin should occur wash with a suitable antiseptic cleaner and then soap and water. If splashes should affect eyes, bathe immediately with copious quantities of clean water and then immediately seek medical advice.

Reference should be made to the separate **ADOCURE SEALER PF** Health and Safety literature.