

EPOMAST THIXOTROPIC FILLER

Description:

A blend of selected fine fillers that can be added to **EPOMAST** epoxy resins to produce a chosen workability.

Typical applications:

- Bedding mortars
- Repair mixes
- Caulking mixes

Advantages:

- Adjustable workability
- Fine grain size for thin sections

Typical data:**Grading:**

122 μm	100%
54.7 μm	96.7%
24.6 μm	75.1%
10.3 μm	43.6%
4.97 μm	19.2%
2.99 μm	5.1%
1.93 μm	1.2%

Average (50%)	12.5m
---------------	-------

Bulk density	820 Kg/m ³
--------------	-----------------------

Acid solubility	4.60%
-----------------	-------

Water solubility	0.10%
------------------	-------

PH	7.10
----	------

Instructions for Use:

EPOMAST THIXOTROPIC FILLER can be used with both **EPOTAC** and **EPOBOND** to produce progressively stiffer mixtures to suit a variety of applications.

Applications include filled adhesives, bedding and caulking mixes.

Mix the resin base according to the instructions on the pack.

Add **EPOMAST THIXOTROPIC FILLER** to the mixed resin and hardener base to adjust the consistency until the desired workability is achieved. When using in a very stiff form it is sometimes advisable to use some of the base pack as a primer/adhesive on the substrate before placing the filled mixture.

Only mix as much as can be used in 30 minutes (less at higher temperatures).

Clean tools with **RESOKLENS (EPOTAC)** or water (**EPOBOND**) before materials have set.

Storage:

Store in dry conditions and keep container sealed when not in use. Shelf life when stored correctly is in excess of 12 months.

Packaging:

4 and 12Kg bags.

Health and safety:

EPOMAST THIXOTROPIC FILLER has a high proportion of fine dust particles and the use of dust masks and goggles is recommended.

Refer to separate **EPOMAST THIXOTROPIC FILLER** Health and Safety sheet.

**Adomast Ltd**

Lea Road Trading Estate, Lea Road, Waltham Abbey, Essex EN9 1AE, England.

Telephone: +44 (0)1992 710684 Fax: +44 (0)1992 712813 Email: sales@adomast.co.uk

www.adomast.co.uk