

Technical Specifications

Rapid & Permanent Repair to Concrete & Masonry Surfaces

Epomast Fastpatch is a high strength, trowel applied, two-component Epoxy resin mortar, Designed for rapid and permanent repairs to concrete and masonry surfaces. Epomast Fastpatch is a blend of Epoxy resin, polyamine curing agent, graded aggregate and colour pigments. The mixed material is applied to a suitably prepared surface and quickly cures to form a durable abrasion and chemical resistant repair. Typical uses repairs to spalled or damaged concrete; chemical bunds; bedding Pre-Cast concrete beams; nosing's on expansion joints; floor repairs.

Advantages

- Pre-packed units – ready to use
- Fast curing characteristics
- Impact and abrasion resistant
- Frost resistant and impervious to water
- Excellent mechanical properties
- Unaffected by a wide range of acids, and industrial chemicals
- Negligible shrinkage
- High bond strength—no primer required
- Cures under damp, cool conditions

Typical Properties Colour: Light grey (other colours available upon request)

Density: 2000kg/m³

Pot Life: 40 minutes @ 20°C

Adhesion to concrete: 3.9MPa (concrete failure)

Compressive Strength: 76MPa

Taber abrasion resistance: 40mg weight loss (CS17 wheels; 1kg loads, 1000 cycles)

Maximum Service Temperature: 70°C continuous

Application

Surface Preparation

Remove all laitance, spalled concrete, grease, oil, dust and other contaminant by scabbing or bush hammering to provide a sound clean substrate. Any exposed reinforcing steel shall be fully exposed by cutting out around its full circumference, and cleaned by abrading or grit blasting to remove, rust, scale, etc

Priming

Primer not normally required. For exceptionally porous surfaces, please contact our technical department for specific advice.

Mixing

Epomast Fastpatch is supplied as a two component pack. Each component is pre-weighed and ready to mix. The contents of the **CURING AGENT** should be added into that containing the **BASE** and the two components thoroughly mixed by spatula or low speed drill/stirrer, or forced action mixer.

Application

Apply the Epomast Fastpatch by tamping and trowelling to ensure good compaction and a tight finish. The material should not be feather edged. Maximum thickness in horizontal applications 150mm. For vertical applications the material may be built up in the layers not exceeding 6mm (See also Epomast Mortar data sheet)

Equipment Cleaning

Clean equipment with Resolens prior to curing of the mortar

Curing and Overcoating

Epomast Fastpatch will have hardened sufficiently after 5-6 hours cure @ 15-20°C to allow full trafficking. Longer periods of cure will be necessary at lower temperatures. Full mechanical and chemical resistance properties will be achieved after 3 days cure @ 20°C. It is preferable to apply a sealer coat if exposure to chemicals is likely.

Please consult our technical department for specific recommendations

Coverage

A 5kg pack of EPOMAST FASTPATCH yields 2.5 litres of material, sufficient for 0.5m² @ 5mm thickness (10kg pack pro-rata)

Do not apply to wet or uncured concrete surfaces. Do not apply at temperatures of 3°C or less

Storage

Store in dry conditions at temperatures between 10°C and 25°C. Avoid low temperature storage prior to use of the material. Do not expose to freezing conditions.

Shelf Life

Epomast Fastpatch has a minimum shelf life of 12 months when stored in original, unopened containers in accordance with manufacturer's instructions

Specification

Epomast Mortar is manufactured by Adomast Manufacturing Ltd and shall be applied in accordance with the manufacturer's instructions

Health and Safety

Wear gloves and goggles.

Wash off splashes immediately with soap and water.

Any eye contamination must be rapidly irrigated with copious amounts of water, and immediate medical attention sought.

Please refer to Material Safety Data Sheet for additional information.

Epomast Fastpatch shall be applied strictly in accordance with the manufacturers instructions.

For specified advice regarding any aspect of this product, please consult our technical department.